

Need Metal? We get it!

SpecMet CSF-309LMo(P)

AWS A5.22 E309LMoT1-1/4
KS D 3612 YF309MoLC
JIS Z 3323 TS309LMo-FB1
EN ISO 17633-A T 23 12 2 L P C1[M21] 1 - ISO 17633-B TS 309LMo-F C1[M21] 1

Applications

CSF-309MoL(P) is suitable for welding of 22%Cr-12%Ni-2%Mo steel and heat resistant steel and dissimilar joint such as a stainless steel to carbon steel of low alloy steel. Under layer welding on clad side groove clad stainless steel or carbon steel where stainless steel weld metal is overlaid.

Characteristics

- (1) CSF-309MoL(P) is flux cored wire and designed for Fillet & H-F(All-position) welding with CO₂ gas Shielding.
- (2) It provides the excellent usability with stable arc, less spattering, good bead appearance, better slag removal, and less quantity of welding fume comparable to solid wire.
- (3) Is containing Ferrite of a reasonable quantity and crack-resistance, intergranular corrosion resistance, mechanical properties of weld metal is superior.
- (4) Shield gas is 100% CO₂ or Ar+CO₂ gas.

Notes on Usage

- (1) The optimum flow of CO₂ for Shielding is 20~25l/min.
- (2) Protect the weld with a screen to prevent blowholes caused by wind where the wind velocity is 2m/sec and more.
- (3) Keep the distance between tip & base metal at 15~25mm.

Typical Chemical Composition of Weld Metal (%) (shielding gas: 100% CO₂)

	C	Mn	Si	P	S	Cr	Ni	Mo	FN
309LMo	0.03	1.4	0.55	0.015	0.010	23.0	13.0	2.5	23
309LMoP	0.03	0.74	0.66	0.017	0.009	22.6	12.8	2.3	22

Typical Mechanical Properties of Weld Metal (%) (shielding gas: 100% CO₂)

	YS N/mm ² (MPa)	TS N/mm ² (MPa)	EL (%)	IV (J) 0° C
309LMo	560	680	33	32
309LMoP	535	695	34	30

Size and Recommended Current Range (AC or DC+)

Dia mm (in)	Current (A)	Volatage (V)	Welding Speed (cm/min)
1.2 (0.045)	150~300	24~33	20~60
1.6 (0.062)	200~400	24~33	20~60

Approval : CSF-309MoL : ABS, LR